

EPDM Hose Chemical Resistance

The information presented here is derived from experimental data and is considered accurate. However, please note that this table should be treated as a general reference only, as it does not account for all potential variables—such as high temperatures, fluid impurities, concentration levels, and other factors—that may arise in real-world applications. It is strongly recommended that testing be conducted for any critical uses.

Note: Unless specified, all data corresponds to a temperature of 20°C (68°F).

Acetaldehyde	Excellent
Acetic Acid, Glacial	Good
Acetic Acid, 10%	Excellent
Acetic Acid, 50%	Excellent
Acetic Anhydride	Good
Acetic Oxide	Good
Acetone	Excellent
Acetone Cyanohydrin	Excellent
Acetonitrile	Excellent
Acetophenone	Excellent
Acetyl Acetone	Excellent
Acetyl Chloride	Unsatisfactory
Acetyl Oxide	Good
Acetylene	Excellent
Acetylene Dichloride	Conditional
Acetylene Tetrachloride	Conditional
Acrolein	Excellent
Acrylonitrile	Excellent
Acrylic Acid	Unsatisfactory
Adipic Acid	Conditional
Air, +300 °F	Good
Alk-Tri	Unsatisfactory
Allyl Alcohol	Excellent
Allyl Bromide	Unsatisfactory
Allyl Chloride	Unsatisfactory
Alum	Good
Aluminium Acetate	Excellent
Aluminium Chloride	Excellent
Aluminium Fluoride	Excellent
Aluminium Formate	Excellent
Aluminium Hydroxide	Excellent
Aluminium Nitrate	Excellent
Aluminium Sulfate	Excellent
Amines-Mixed	Good
Aminobenzene	Conditional
Aminodimethylbenzene	Conditional
Aminoethane	Excellent
Aminoxylene	Excellent
Ammonium Carbonate	Excellent
Ammonium Chloride	Excellent
Ammonium Hydroxide	Excellent
Ammonium Nitrate	Excellent
Ammonium Phosphate, Dibasic	Excellent
Ammonium Sulfate	Excellent
Ammonium Sulfide	Excellent
Ammonium Thiosulfate	Excellent
Amyl Acetate	Conditional
Amyl Acetone	Good
Amyl Alcohol	Excellent
Amyl Bromide	Conditional
Amyl Chloride	Unsatisfactory
Amyl Ether	Unsatisfactory
Amylamine	Unsatisfactory
Anethole	Unsatisfactory
Aniline	Conditional

Aniline Dyes	Conditional
Aniline Oil	Conditional
Animal Fats	Conditional
Antimony Pentachloride	Conditional
Aqua Regia	Conditional
Argon	Excellent
Arsenic Acid	Excellent
Asphalt	Unsatisfactory
ASTM Fuel A	Unsatisfactory
ASTM Fuel B	Unsatisfactory
ASTM Fuel C	Unsatisfactory
ASTM Oil No.1	Unsatisfactory
ASTM Oil No.2	Unsatisfactory
ASTM Oil No.3	Unsatisfactory
ASTM Oil No.4	Unsatisfactory
Automatic Transmission Fluid	Unsatisfactory
Banana Oil	Conditional
Barium Chloride	Excellent
Barium Hydroxide	Excellent
Barium Sulphide	Excellent
Beer	Excellent
Beet Sugar Liquors	Excellent
Benzal Chloride	No data
Benzaldehyde	Excellent
Benzene	Conditional
Benzene Carboxylic Acid	Conditional
Benzine	Unsatisfactory
Benzoic Acid	Conditional
Benzol	Conditional
Benzotrichloride	Excellent
Benzyl Acetate	Excellent
Benzyl Alcohol	Conditional
Benzyl Chloride	Unsatisfactory
Benzyl Ether	Conditional
Black Sulfate Liquor	Good
Bleach	Excellent
Borax Solution	Excellent
Boric Acid	Excellent
Brake Fluid (Hd-557)12 Days	Excellent
Brine	Excellent
Bromobenzene	Unsatisfactory
Bromochloromethane	Good
Bromoethane	Unsatisfactory
Bromotoluene	No data
Bunker Oil	Unsatisfactory
Butadiene	Unsatisfactory
Butane	Unsatisfactory
Butanoic Acid	Conditional
Butanol	Conditional
Butanone	Excellent
Butoxyethanol	Excellent
Butyl Acetate	Conditional
Butyl Acrylate	Conditional
Butyl Alcohol	Conditional
Butyl Aldehyde	Conditional

EPDM Hose Chemical Resistance

Butyl Benzyl Phthalate	Excellent
Butyl Carbitol	Excellent
Butyl Cellosolve	Conditional
Butyl Chloride	Unsatisfactory
Butyl Ether	Conditional
Butyl Ether Acetaldehyde	Unsatisfactory
Butyl Ethyl Ether	Fair
Butyl Oleate	Conditional
Butyl Phthalate	Excellent
Butyl Stearate	Unsatisfactory
Butylene	Unsatisfactory
Butyraldehyde	Conditional
Butyric Acid	Conditional
Butyric Anhydride	Excellent
Cadmium Acetate	No data
Calcium Aluminate	No data
Calcium Bichromate	Excellent
Calcium Bisulfide	Excellent
Calcium Chloride	Excellent
Calcium Hydroxide	Excellent
Calcium Hypochlorite	Excellent
Calcium Nitrate	Excellent
Calcium Sulfide	Excellent
Calcium Acetate	Excellent
Caprylic Acid	No data
Carbamide	Excellent
Carbitol	Conditional
Carbolic Acid Phenol	No data
Carbon Dioxide	Good
Carbon Disulfide	Unsatisfactory
Carbon Monoxide	Excellent
Carbon Tetrachloride	Unsatisfactory
Carbonic Acid	Excellent
Castor Oil	Conditional
Caustic Soda	Good
Cellosolve Acetate	Good
Cellugard	Excellent
Cetylic Acid	Conditional
China Wood Oil	Unsatisfactory
Chlorinated Solvents	Unsatisfactory
Chloro-2-Propanone	No data
Chloroacetic Acid	Conditional
Chloroacetone	Excellent
Chlorobenzene	Unsatisfactory
Chlorobutane	Unsatisfactory
Chlorodane	Unsatisfactory
Chloroethyl Benzene	Unsatisfactory
Chloroform	Unsatisfactory
Chloropentane	Unsatisfactory
Chlorosulfonic Acid	Unsatisfactory
Chlorotoluene	Unsatisfactory
Chlorox	Good
Chrome Plating Solutions	Conditional
Chromic Acid	Conditional
Chromium Trioxide	Conditional
Cinnamene	Unsatisfactory
Cis-9-Octadecenoic Acid	Conditional
Citric Acid	Excellent
Coal Tar Oil	Unsatisfactory
Coal Tar	Unsatisfactory
Coal Tar Naphtha	Unsatisfactory
Coconut Oil	Conditional
Coke Oven Gas	Unsatisfactory
Coolanol	Unsatisfactory
Copper Chloride	Excellent

Copper Cyanide	Excellent
Copper Hydrate	No data
Copper Hydroxide	No data
Copper Sulfate	Excellent
Corn Oil	Conditional
Cottonseed Oil	Conditional
Creosote	Unsatisfactory
Cresols	Unsatisfactory
Cresylic Acid	Unsatisfactory
Crotonaldehyde	Excellent
Crude Oil	Unsatisfactory
Cumene	Unsatisfactory
Cupric Hydroxide	No data
Cupric Nitrate	Conditional
Cupric Sulfate	Excellent
Cutting Oil	Unsatisfactory
Cyclohexane	Unsatisfactory
Cyclohexanol	Unsatisfactory
Cyclohexanone	Conditional
Cyclopentane	Unsatisfactory
Cyclopentanone	No data
Cyclopentil Alcohol	Conditional
D-Furaldehyde	Excellent
Ddt In Kerosene	Unsatisfactory
Decahydronaphthalene	Unsatisfactory
Decalin	Unsatisfactory
Decyl Alcohol	Unsatisfactory
Decyl Aldehyde	Unsatisfactory
Decyl Butyl Phthalate	No data
Detergent, Water Solution	Excellent
Developing Fluid	Conditional
Dextron	Unsatisfactory
Di (2Ethylhexyl) Adipate	Good
Di (2Ethylhexyl) Phthalate	Conditional
Di-Iso-Butylene	Conditional
Di-Iso-Decyl Phthalate	Excellent
Di-Iso-Propanolamine	Excellent
Di-Iso-Propyl Ether	Unsatisfactory
Di-Iso-Propyl Ketone	Excellent
Di-P-Mentha-1,8-Diene	Unsatisfactory
Diacetone Alcohol	Excellent
Diacetylmethane	Excellent
Diammonium Orthophosphate	Excellent
Diamyl Naphthalene	No data
Diamylamine	Excellent
Diamylene	Unsatisfactory
Diamylphenol	No data
Dibenzyl Ether	Conditional
Dibromobenzene	Unsatisfactory
Dibromomethane	Conditional
Dibutyl Ether	Conditional
Dibutyl Phthalate	Conditional
Dibutyl Sebacate	Conditional
Dibutylamine	Fair
Dicalcium Phosphate	Excellent
Dichloroethylene	Conditional
Dichloroacetic Acid	Unsatisfactory
Dichlorobenzene	Unsatisfactory
Dichlorobutane	Unsatisfactory
Dichlorodifluoromethane	Conditional
Dichloroethane	Unsatisfactory
Dichloroethyl Ether	Unsatisfactory
Dichlorohexane	Unsatisfactory
Dichloromethane	Unsatisfactory

EPDM Hose Chemical Resistance

Dichloropentane	Unsatisfactory
Dichloropropane	Unsatisfactory
Dichloropropene	Unsatisfactory
Diesel Oil	Unsatisfactory
Diethanol Amine	Good
Diethylbenzene	No data
Diethyl Ether	Unsatisfactory
Diethyl Ketone	Good
Diethyl Oxalate	Unsatisfactory
Diethyl Phthalate	Fair
Diethyl Sebacate	Fair
Diethyl Sulfate	Excellent
Diethyl Amine	Conditional
Diethylene Glycol	Excellent
Diethylene Oxide	Excellent
Diethylenetriamine	Excellent
Dihydroxy Succinic Acid	Good
Dihydroxydiethyl Ether	Excellent
Dijisobutyl Ketone	Excellent
Dijisodecyl Phthalate	Excellent
Dijsooctyl Adipate	Excellent
Dijsooctyl Phthalate	Good
Dimethyl Carbinol	Excellent
Dimethyl Ketone	Excellent
Dimethyl Phthalate	Conditional
Dimethyl Sulfate	Unsatisfactory
Dimethyl Sulfide	Unsatisfactory
Dimethylamine	Excellent
Dimethylaniline	Excellent
Dimethylbenzene	Unsatisfactory
Dimethylbutane	No data
Dioxane	Conditional
Dipentene	Unsatisfactory
Dipentylamine	Excellent
Dipropylene Glycol	Excellent
Disodium Phosphate	Excellent
Divinyl Benzene	Unsatisfactory
Dowthermn, A And E	Unsatisfactory
Dry Cleaning Fluids	Unsatisfactory
Ethanoic Acid	Conditional
Ethanol	Excellent
Ethanolamine	Excellent
Ethers	Unsatisfactory
Ethyl Acetate	Conditional
Ethyl Acetoacetate	Conditional
Ethyl Acetone	Good
Ethyl Acrylate	Conditional
Ethyl Alcohol	Excellent
Ethyl Aldehyde	Excellent
Ethyl Aluminium Dichloride	No data
Ethyl Benzene	Unsatisfactory
Ethyl Bromide	Unsatisfactory
Ethyl Butyl Acetate	No data
Ethyl Butyl Alcohol	No data
Ethyl Cellulose	Conditional
Ethyl Chloride	Conditional
Ethyl Dichloride	Unsatisfactory
Ethyl Ether	Unsatisfactory
Ethyl Formate	Conditional
Ethyl Iodide	Fair
Ethyl Oxalate	Excellent
Ethyl Phthalate	Fair
Ethyl Silicate	Excellent
Ethyl-N-Butyl Ketone	No data

Ethyl-1-Butanol	Excellent
Ethylamine	Excellent
Ethylene Chlorohydrin	Conditional
Ethylene Diamine	Excellent
Ethylene Dibromide	Conditional
Ethylene Dichloride	Unsatisfactory
Ethylene Glycol Monobutyl Ether	Excellent
Ethylene Glycol Monoethyl Ether	Conditional
Ethylene Glycol	Excellent
Ethylene Oxide	Conditional
Fatty Acids	Unsatisfactory
Ferric Bromide	No data
Ferric Chloride	Excellent
Ferric Nitrate	Excellent
Ferric Sulfate	Excellent
Ferrous Acetate	Good
Ferrous Chloride	Excellent
Ferrous Sulfate	Excellent
Fluoroboric Acid	Excellent
Fluorine	Excellent
Fluorosilicic Acid	Excellent
Formaldehyde	Conditional
Formalin	Excellent
Formic Acid	Excellent
Freon 113	Unsatisfactory
Freon 12	Conditional
Freon 22	Conditional
Fuel A	Unsatisfactory
Fuel B	Unsatisfactory
Fuel Oil	Unsatisfactory
Furan	Unsatisfactory
Furfural	Conditional
Fuel A (Astm)	Unsatisfactory
Fuel B (Astm)	Unsatisfactory
Fuel Oil	Unsatisfactory
Furan	Unsatisfactory
Furfural	Conditional
Furfuran	Unsatisfactory
Furfuryl Alcohol	Conditional
Gallic Acid	Conditional
Gallotannic Acid	Excellent
Gasoline	Unsatisfactory
Glacial Acrylic Acid	Unsatisfactory
Gluconic Acid	Excellent
Glucose	Excellent
Glycerine	Excellent
Glycerol	Excellent
Glycogenic Acid	Excellent
Glycols	Excellent
Glyconic Acid	Excellent
Glycyl Alcohol	No data
Grease	Unsatisfactory
Green Sulphate Liquor	Excellent
Helium	Excellent
Heptaldehyde	Conditional
Heptanal	Conditional
Heptane	Unsatisfactory
Heptanoic Acid	Unsatisfactory
Hexadecanoic Acid	Good
Hexaldehyde	Conditional
Hexane	Unsatisfactory
Hexanol	Excellent
Hexene	No data
Hexyl Alcohol	Excellent

EPDM Hose Chemical Resistance

Hexyl Methyl Ketone	Good
Hexylamine	Good
Hexylene Glycol	Fair
Histowax	No data
Hydraulic & Motor Oil	Conditional
Hydrazine	Excellent
Hydrobromic Acid	Excellent
Hydrochloric Acid	Conditional
Hydrocyanic Acid	Excellent
Hydrofluoric Acid	Conditional
Hydrofluosilicic Acid	Excellent
Hydrogen Chloride Anhydrous	Excellent
Hydrogen Dioxide	Good
Hydrogen Gas	Excellent
Hydrogen Peroxide Over 10%	Conditional
Hydrogen Peroxide 10%	Good
Hydrogen Sulfide	Excellent
Hydroxy Benzene	Conditional
Hydroxyisobutyronirile	Excellent
Hydroxytoluene	Conditional
Iminodi-2-Propanol	Excellent
Iminodiethanol	Good
Iodine	Conditional
Iodine Pentafluoride	Unsatisfactory
Iodoform	Excellent
Iso-Butanal	Good
Iso-Butylamine	Excellent
Iso-Butylbromide	Conditional
Iso-Butylcarbinol	Excellent
Isocyanates	Conditional
Isooctane	Excellent
Isopropyl Acetate	Good
Isopropyl Alcohol	Conditional
Isopropyl Ether	Unsatisfactory
Jet Fuels	Excellent
Jp-4 Oil	Good
Kerosene	Good
Ketones	Unsatisfactory
Lacquer Solvents	Excellent
Lactic Acid - Cold	Good
Lactic Acid - Hot	Unsatisfactory
Lard	Conditional
Lavender Oil	Excellent
Lead Acetate	Unsatisfactory
Lead Nitrate	Unsatisfactory
Lead Sulfate	Unsatisfactory
Lime	Unsatisfactory
Lime Bleach	Excellent
Lime Sulfur	Excellent
Limonene	Conditional
Linoleic Acid	Unsatisfactory
Linseed Oil	Conditional
Liquid Petroleum Gas	Unsatisfactory
Lubricating Oil	Unsatisfactory
Lye Solutions	Good
Mek	Excellent
Magnesium Acetate	Good
Magnesium Chloride	Excellent
Magnesium Hydrate	Excellent
Magnesium Hydroxyde	Excellent
Magnesium Sulfate	Excellent
Malpic Acid	Conditional
Malpic Anhydride	Conditional
Malic Acid	Conditional
Manganous Sulfate	Excellent

Mercury	Excellent
Mercury Vapors	Excellent
Mestiyi Oxide	Conditional
Methallyl Alcohol	Excellent
Methallyl Chloride	No data
Methane Carboxylic Acid (See Acetic Acid)	No data
Methanoic Acid	Excellent
Methanol	Excellent
Methoxy Ethanol	Excellent
Methyl Acetate	Conditional
Methyl Acetoacetate	Conditional
Methyl Acetone	Excellent
Methyl Allyl Chloride	No data
Methyl Amyl Carbinol	Excellent
Methyl Benzene	Unsatisfactory
Methyl Bromide	Unsatisfactory
Methyl Butane	Unsatisfactory
Methyl Butyl Ketone	Excellent
Methyl Carbitol	Good
Methyl Cellosolve	Conditional
Methyl Chloride	Conditional
Methyl Cyanide	Excellent
Methyl Ethyl Ketone	Excellent
Methyl Hexanol	Excellent
Methyl Methacrylate	Unsatisfactory
Methyl Normal Amyl Ketone	Excellent
Methyl Propyl Ether	Unsatisfactory
Methyl Salicylate	Conditional
Methyl Styrene	Unsatisfactory
Methyl Sulfide	Unsatisfactory
Methyl-iso-Amyl-Ketone	No data
Methyl-2-Butanone	Conditional
Methyl-2-Hexanone	No data
Methyl-2-Pentanol	Excellent
Methyl-2-Pentanone	Conditional
Methyl-4-Isopropyl Benzene	Unsatisfactory
Methyl Amyl Acetate	No data
Methyl Amyl Alcohol	Excellent
Methylcyclohexane	Unsatisfactory
Methylene Bromide	Unsatisfactory
Methylene Chloride	Conditional
Methylethyl Ketone	Excellent
Methyl Hexyl Ketone	Good
Methyl Isobutyl Carbinol	Conditional
Methylisobutyl Ketone	Conditional
Methylisopropyl Ketone	Conditional
Methylactonitrile	Excellent
Methylpropyl Carbinol	No data
Methylpropyl Ketone	Good
Mineral Oil	Unsatisfactory
Mineral Spirits	Unsatisfactory
Mobile Hf A	Unsatisfactory
Molten Sulfur	Excellent
Mono-Chloroacetic Acid	Good
Monobutyl Ether	Conditional
Monochlorobenzene	Unsatisfactory
Monochlorodifluoromethane	Conditional
Monoethanol Amine	Conditional
Monoethyl Amine	Excellent
Morpholine	Conditional
Motor Oil, 40W	Unsatisfactory
Mtbe	No data
Muriatic Acid	Fair
N-Butanal	Conditional
N-Butylamine	Conditional

EPDM Hose Chemical Resistance

N-Butylbenzene	Unsatisfactory
N-Butylbromide	Unsatisfactory
N-Butylbutyrate	Excellent
N-Butylcarbinol	Excellent
N-Nonyl Alcohol	Excellent
N-Octane	Unsatisfactory
Naphtha	Unsatisfactory
Naphthalene	Unsatisfactory
Naphthenic Acid	Unsatisfactory
Natural Gas	Unsatisfactory
Neohexane	Unsatisfactory
Neon Gas	Excellent
Neu-Tri	No data
Nickel Acetate	Excellent
Nickel Chloride	Excellent
Nickel Nitrate	Excellent
Nickel Sulfate	Excellent
Nitric Acid, Conc	Unsatisfactory
Nitric Acid, Red Fuming	Unsatisfactory
Nitric Acid, 10%	Excellent
Nitric Acid, 13N	No data
Nitric Acid, 13N +5%	No data
Nitric Acid, 20%	Excellent
Nitric Acid, 30%	Fair
Nitric Acid, 30% - 70%	Unsatisfactory
Nitriotriethanol	Excellent
Nitrobenzene	Conditional
Nitroethane	Conditional
Nitrogen	Excellent
Nitromethane	Conditional
Nitrous Oxide Gas	Excellent
Nonanoic Acid	No data
Nonanol	Excellent
Octanoic Acid	No data
Octanol	Conditional
Octyl Acetate	Good
Octyl Alcohol	Conditional
Octyl Aldehyde	No data
Octyl Amine	Good
Octyl Carbinol	Excellent
Octylene Glycol	Excellent
Oil-Petroleum	No data
Oleic Acid	Unsatisfactory
Oleum	Unsatisfactory
Olive Oil	Good
Ortho-Dichlorobenzene	Unsatisfactory
Ortho-Dichlorobenzol	Unsatisfactory
Orthoxylene	Unsatisfactory
Oxalic Acid	Excellent
Ozone	Excellent
P-Cymene	Unsatisfactory
Paint Thinner	Unsatisfactory
Palmitic Acid	Conditional
Papermakers Alum	No data
Para-Dichlorobenzene	Unsatisfactory
Paraffin Wax	Unsatisfactory
Paraldehyde	Excellent
Paraxylene	Unsatisfactory
Pelargonic Alcohol	Excellent
Pentachloroethane	No data
Pentamethylene	Unsatisfactory
Pentane	Unsatisfactory
Pentanol	No data
Pentanone	Good
Pentasol	Good

Pentyl Acetate	Conditional
Pentyl Alcohol	Excellent
Pentyl Bromide	Conditional
Pentyl Chloride	Unsatisfactory
Pentyl Ether	Unsatisfactory
Pentylamine	Unsatisfactory
Perchloric Acid	Good
Perchloroethylene	Unsatisfactory
Perchloromethane	Unsatisfactory
Petroleum Crude	Unsatisfactory
Petroleum Ether	Unsatisfactory
Petroleum Oils	Unsatisfactory
Phenol	Unsatisfactory
Phenolsulfonic Acid	Excellent
Phenylamine	Conditional
Phenylbromide	No data
Phenylmethane	Unsatisfactory
Phenylmethanol	Conditional
Phosphate Esters	Excellent
Phosphoric Acid 10%	Excellent
Phosoric Acid 10% - 85%	Excellent
Phosphorus Trichloride	Excellent
Picric Acid, H2O Solution	Excellent
Pine Oil	Unsatisfactory
Pinene	Unsatisfactory
Polyethylene Glycol E-400	Excellent
Polyl Enter	Unsatisfactory
Polypropylene Glycol	No data
Potassium Acetate	Excellent
Potassium Bisulfate	Excellent
Potassium Bisulfite	Excellent
Potassium Carbonate	Excellent
Potassium Chloride	Excellent
Potassium Chromate	Excellent
Potassium Cyanide	Excellent
Potassium Dichromate	Excellent
Potassium Hydrate	No data
Potassium Hydroxyde	Excellent
Potassium Nitrate	Excellent
Potassium Permanganate, 5%	Excellent
Potassium Silicate	Excellent
Potassium Sulfate	Excellent
Potassium Sulfide	Excellent
Potassium Sulfite	Excellent
Prestone Antifreeze	Excellent
Producer Gas	Unsatisfactory
Propane	Unsatisfactory
Propanediol	Excellent
Propanetriol	Excellent
Propanol	Excellent
Propanone	Excellent
Propenol	No data
Propanediamine	No data
Propene Nitrile	No data
Propenyl Alcohol	Excellent
Propenyl Anisole	No data
Propionic Acid	Excellent
Propionitrile	Conditional
Propyl Acetate	Conditional
Propyl Alcohol	Excellent
Propyl Aldehyde	Good
Propyl Benzene	No data
Propyl Chloride	Fair
Propyl Nitrate	Conditional
Propylene	Unsatisfactory

EPDM Hose Chemical Resistance

Propylene Diamine	No data
Propylene Glycol	Excellent
Pydraul, 'E' Series	Conditional
Pydraulic 'C'	Unsatisfactory
Red Oil	Fair
Refrigerant 11	No data
Refrigerant 12	No data
Refrigerant 22	No data
Resorcinol	Good
Sae No. 10 Oil	Unsatisfactory
Sal Ammoniac	Excellent
Sea Water	Excellent
Sewage	Good
Silicate Esters	Unsatisfactory
Silicate Of Soda	Excellent
Silicone Grease	Excellent
Silicone Oil	Excellent
Silver Nitrate	Excellent
Skydrol 500 Type 2	Excellent
Skydrol 500B	Excellent
Skydrol 500C	Excellent
Skydrol 7000 Type 2	Excellent
Soap Solutions	Excellent
Soda Ash	Excellent
Soda Lime	Excellent
Soda Niter	Excellent
Sodium Acetate	Excellent
Sodium Aluminate	Excellent
Sodium Bicarbonate	Excellent
Sodium Bisulfate	Excellent
Sodium Bisulfite	Excellent
Sodium Borate	Excellent
Sodium Carbonate	Excellent
Sodium Chloride	Excellent
Sodium Cyanide	Excellent
Sodium Dichromate	Excellent
Sodium Hydrate	Excellent
Sodium Hydrochlorite	Good
Sodium Hydroxide	Excellent
Sodium Hypochlorite	Excellent
Sodium Metaphosphate	Excellent
Sodium Nitrate	Excellent
Sodium Perborate	Excellent
Sodium Peroxide	Excellent
Sodium Phosphate	Excellent
Sodium Silicate	Excellent
Sodium Sulfate	Excellent
Sodium Sulfide	Excellent
Sodium Sulfite	Excellent
Sodium Thiosulfate	Excellent
Soybean Oil	Conditional
Stannic Chloride	Excellent
Stannic Sulfide	Excellent
Stannous Chloride	Good
Stannous Sulfide	Excellent
Steam, Below 350 Deg F	Excellent
Stearic Acid	Good
Stoddard Solvent	Unsatisfactory
Styrene	Unsatisfactory
Sulfamic Acid	Excellent
Sulfur	Excellent
Sulfur Chloride	Excellent
Sulfur Dioxide	Excellent
Sulfur Trioxide, Dry	Excellent
Sulfuric Acid 60%	Excellent

Sulfuric Acid, Conc.	Unsatisfactory
Sulfuric Acid, Fuming	Unsatisfactory
Sulfuric Acid, 25%	Excellent
Sulfuric Acid, 25%-50%	Excellent
Sulfuric Acid, 50%-96%	Unsatisfactory
Sulfurous Acid, 10%	Excellent
Sulfurous Acid, 10%-75%	Excellent
T-Butyl Amine	Conditional
Tall Oil	Unsatisfactory
Tallow	Excellent
Tannic Acid	Excellent
Tar	Unsatisfactory
Tar Bituminous	Unsatisfactory
Tartaric Acid	Good
Tellone 2	No data
Tertiary Butyl Alcohol	Conditional
Terpineol	No data
Tertiary Butyl Amine	Conditional
Tertiary Butyl Mercaptan	Unsatisfactory
Tetrachlorobenzene	Unsatisfactory
Tetrachloroethane	Unsatisfactory
Tetrachloroethylene	Unsatisfactory
Tetrachloromethane	Unsatisfactory
Tetrachloronaphthalene	Unsatisfactory
Tetraethylene Glycol	Excellent
Tetraethylorthosilicate	Excellent
Tetrahydrofuran	Unsatisfactory
Tin Chloride	Excellent
Titanium Tetrachloride	Unsatisfactory
Toluene	Unsatisfactory
Toluidine	Unsatisfactory
Toluol	Unsatisfactory
Transformer Oil	Unsatisfactory
Transmission 'A' Oil	Unsatisfactory
Tri-Amine	Excellent
Tributyl Phosphate	Good
Tributylamine	No data
Trichloroacetic Acid	Conditional
Trichlorobenzene	Unsatisfactory
Trichloroethane	Unsatisfactory
Trichloroethylene	Unsatisfactory
Trichloromethane	Unsatisfactory
Trichlorotoluene	Excellent
Tricresyl Phosphate	Excellent
Triethanolamine	Excellent
Triethylamine	Excellent
Triethylene Glycol	Excellent
Trihydroxybenzoic Acid	Conditional
Trimethyl Pentane	Unsatisfactory
Trimethylamine	Conditional
Trisodium Phosphate	Excellent
Tritoyl Phosphate	Excellent
Tung Oil	Unsatisfactory
Turpentine	Unsatisfactory
Unsymmetrical Dimethyl Hydrazine	Excellent
Undecyl Alcohol	Excellent
Urea	Excellent
Uric Acid	Excellent
Varnish	Unsatisfactory
Vegetable Oils	Fair
Versilube F44	Excellent
Versilube F55	Unsatisfactory
Vinegar	Excellent
Vinegar Acid	No data

EPDM Hose Chemical Resistance

Vinyl Acetate	Good
Vinyl Benzene	Unsatisfactory
Vinyl Chloride	Excellent
Vinyl Cyanide	Unsatisfactory
Vinyl Ether	No data
Vinyl Toluene	Unsatisfactory
Vinyl Trichloride	Unsatisfactory
Vm & Naphtha	Unsatisfactory
Water	Excellent
Water, Boiling	Excellent
Water, Soda	No data
Wemco C	Unsatisfactory
Whiskey	Excellent
White Oil	Unsatisfactory
White Pine Oil	Unsatisfactory
Wines	Excellent
Wood Alcohol	Excellent
Wood Oil	Unsatisfactory
Xenon	Excellent
Xylene, Xylon	Unsatisfactory
Xylidine	Good
Zeolites	Excellent
Zinc Acetate	Excellent
Zinc Carbonate	Excellent
Zinc Chloride	Excellent
Zinc Chromate	Excellent
Zinc Sulfate	Excellent
O-Aminotoluene	Conditional
1 Undecanol	Excellent
1-Amino-2-Propanol	Excellent
1-Aminobutane	Conditional
1-Aminopentane	Unsatisfactory
1-Bromo-2-Methyl Propane	Unsatisfactory
1-Bromo-3-Methyl Butane	Unsatisfactory
1-Bromobutane	Unsatisfactory
1-Chloro-2-Methyl Propane	Unsatisfactory
1-Chloro-3-Methyl Butane	Unsatisfactory
1-Decanol	Unsatisfactory
1-Hendecanol	Excellent
1,4-Dioxane	Conditional
2(2Aminoethylamino)Ethanol	No data
2(2Ethoxyethoxy) Ethanol	Conditional
2(2Ethoxyethoxy) Ethyl Acetate	Unsatisfactory
2-Aminoethanol	Excellent
2-Chloro-1-Hydroxy-Benzene	Unsatisfactory
2-Chlorophenol	Unsatisfactory
2-Chloropropane	Unsatisfactory
2-Ethoxyethanol	Conditional
2-Ethoxyethyl Acetate	Good
2-Ethyl	No data
2-Ethyl-1-Hexanol	Conditional
2-Ethylhexanoic Acid	No data
2-Ethylhexyl Acetate	Conditional
2-Octanone	Good
3-Bromopropene	Unsatisfactory
3-Chloropropene	Unsatisfactory
3-Coal Oil	Unsatisfactory
4-Hydroxy-4-Methyl-2-Pentanone	Excellent